Oxide and chalcogenide nanoparticles from hydrothermal/solvothermal reactions

Michael Rajamathi^a, Ram Seshadri^{b,*}

^aDepartment of Chemistry, St. Joseph's College, Bangalore 560 027, India

^bSolid State and Structural Chemistry Unit, Indian Institute of Science, Bangalore 560 012, India

Abstract

We review recent reports of solvothermal or hydrothermal procedures for the preparation of isolated nanoparticles of some important oxide and chalcogenide materials. The synthetic procedures listed here have the advantages of being relatively inexpensive in terms of the solvents used, arguably green (when water is the solvent) and amenable to scale-up. Handling or processing under inert conditions are rarely called for. We include descriptions of work involving the preparation of capped quantum dots using solvothermal techniques as well as microwave-hydrothermal routes and flow-hydrothermal routes that allow continuous and rapid processing of nanoparticulate materials. © 2002 Elsevier Science Ltd. All rights reserved.

1. Introduction

As the science of nanoparticles matures, there is inevitably great emphasis being placed on scaling up procedures for their syntheses. Most procedures for the preparation of oxide and chalcogenide nanoparticles are solution-based, and often involve reactions carried out near the boiling point of the solvent. In order to obtain crystalline, monodisperse nanoparticles, it is usually necessary to work at relatively high temperatures. This is where a solvent such as trioctyl phosphine oxide (TOPO) is useful for the preparation of semiconductor quantum dots [1], certain transition metal oxide nanoparticles [2] and metal nanoparticles [3]. In these examples, TOPO acts both as solvent and capping agent. In a similar vein, Alivisatos and coworkers [4] have used trioctylamine to thermolyse metal complexes so as to obtain the corresponding oxide nanoparticles.

The problem with these high-temperature solvents, apart from their toxicity, is that they can be very expensive, which makes scale-up non-viable. Handling them (for example, attempting to distill/evaporate/purify) is also not always easy. On the other hand, more common, inexpensive laboratory solvents also cause problems due to the limitations caused by their rather low boiling points. However, a simple method to circumvent this problem lies

in using a solvent well-above its boiling point, i.e. the solvent is heated in a sealed vessel (autoclave, bomb, etc.), so that the autogenous pressure far exceeds the ambient pressure. This automatically raises the effective boiling point of the solvent. Such a technique (which we refer to henceforth as *solvothermal*) is indeed extensively used in the preparation of inorganic solids, and in particular of zeolite materials [5]. In the special case of the solvent being water, the technique is often called *hydrothermal*. In our working definition, we do not require the system to be *supercritical* and indeed, in most solvothermal syntheses, the temperature employed is well below the critical temperature.

In this review, we limit ourselves to the uses of hydro/solvothermal techniques for the preparation of nanoparticles of oxides and chalcogenides. For the most part, our interest is in *unsupported* nanoparticles and we have attempted to focus on procedures that: (i) either involve capping by surfactant, or at least, suggest the possibility for doing so; and/or (ii) result in sub-10 nm particles. We do not discuss the extensive literature on the hydrothermal sol-gel processing of nanophase ceramic materials [6]. To use this review, we suggest that the reader turns to Table 1 and selects either the material of choice, or the solvothermal conditions and then proceeds to find the section under the different subheadings. We have attempted to order the table in the same manner that the material is presented in the text so that relating table contents with text is made easier.

*Corresponding author. Fax: +91-80-360-1310.

E-mail address: seshadri@sscu.iisc.ernet.in (R. Seshadri).

Table 1

Compound	Size (nm)	Starting materials	Solvent	Reference
<i>Oxides</i>				
CeO ₂	2	Ce	2-Methoxyethanol	[*9]
ZnGa ₂ O ₄	10	Zn, GaCl ₃	H ₂ O	[10]
TiO ₂	Sub-100	Ti(OR) ₄	H ₂ O	[**11]
TiO ₂		TiCl ₄	H ₂ O	[12]
TiO ₂	4	TiCl ₄	H ₂ O	[13]
ZrO ₂	3–5	Zr(OR) ₄	Ethanol	[14]
ZnGa ₂ O ₄	5–25	ZnSO ₄ , GaSO ₄	H ₂ O	[15]
TiO ₂	50	Ti(OR) ₄	H ₂ O, cyclohexane	[16]
γ-Fe ₂ O ₃ , CoFe ₂ O ₄	7–12, 7	Co, Fe cupferron complexes	Toluene	[*17]
<i>Chalcogenides</i>				
ZnSe	12–16	Zn, Se	Pyridine	[21]
ZnSe, CdSe	70–100	Zn/Cd, Se	H ₂ O	[*22]
ZnSe	18	Zn, Se	Ethylenediamine	[23]
CdS	6	Cd nitrate or sulphate, thiourea	Ethylene glycol	[24]
CdSe	3	Cd stearate, Se	Toluene	[*25]
Cu _{2–x} Se	18	CuI, Se	Ethylenediamine	[27]
Co ₉ S ₈	6	Co(CH ₃ COO) ₂ , thiourea, hydrazine	H ₂ O	[28]
SnSe	45	SnCl ₂ , Se, Na	Ethylenediamine	[29]
Bi ₂ Se ₃	25	BiCl ₃ , Se, NaI	Ethylenediamine	[30]
In ₂ S ₃	15	InCl ₃ , Na ₂ S ₂ O ₃ (CTAB)	Ethanol	[31]
MSe ₂ (M=Ni, Co, Fe)		MCl ₂ , hydrazine, Se	H ₂ O or DMF	[32]
ME ₂ (M=Ni, Co, Fe, Mo)		MCl ₂ , Na ₂ ESO ₃ (E=S, Se)	H ₂ O	[*33]
CuInSe ₂	15	CuCl ₂ , InCl ₃ , Se	Diethylamine	[34]
CuIn(S,Se) ₂	15	CuCl ₂ , InCl ₃ , S, Se	Ethylenediamine	[35]
AgMS ₂ (M=In, Ga)	6, 10	AgCl, M, S	Ethylenediamine	[36]
CuMS ₂ (M=In, Ga)	10, 35	CuCl, M, S	H ₂ O	[37]
Mn-doped ZnS	12	MCl ₂ , Na ₂ S	H ₂ O, pet. ether	[38]

2. Autogenous pressures in solvothermal reactions

It is useful to be able to estimate the pressures generated within a solvothermal reaction bomb—if only for reasons of safety. Cubic equations of state [7] turn out to be appropriate for this purpose. For a given temperature T and pressure p , they yield three volume roots. The smallest real root corresponds to the molar volume V_m of the liquid fraction in the bomb. Plots of isobars (constant pressure) of the molar volume as a function of temperature can be calculated from these equations. The starting molar volume of the liquid is calculated using the formula weight of the liquid, the filling fraction in the bomb and the volume of the bomb. This molar volume is then interpolated into the plot in order to obtain an estimate of the kinds of pressure being developed in the bomb. We have used the Peng–Robinson equation of state for the purpose. This equation takes the form [8]:

$$p = [RT/(V_m - b)] - [a/(V_m^2 + 2bV_m - b^2)]$$

The parameters a and b are given by:

$$a = 0.45724R^2T_C^2[1 + f_\omega(1 - T_r^{1/2})]^2/p_C$$

$$b = 0.07780RT_C/p_C$$

where $f_\omega = 0.37464 + 1.54226\omega - 0.26992\omega^2$.

The subscript 'r' refers to reduced conditions (for example, $T_r = T/T_C$) and the subscript 'C' denotes the critical value. T_C , p_C and the acentric factor ω are tabulated for many different solvents, for example in the textbook of Reid et al. [8]. Fig. 1 displays the isobars of the molar volume of toluene at different temperatures calculated using the above procedure. We interpret the plot as follows: For a filling fraction of 0.7 of toluene in the bomb, we obtain a molar volume of approximately 0.15 l mol⁻¹. This means, at 250 °C, the pressure within the bomb is approximately 100 bar. At lower temperatures, or smaller filling fractions, the pressure is less.

3. Oxide nanoparticles

As mentioned previously, we focus on solvothermal (including hydrothermal) routes to the *preparation* of unsupported oxide nanoparticles. We do not review the rather extensive literature on the hydrothermal sol–gel *processing*.

3.1. Routes involving oxidation

Metal powders are easily oxidized under solvothermal

Fig. 1. Isobars displaying the dependence of the starting molar volume of toluene taken in a closed bomb, on the temperature. The isobars were obtained using the Peng–Robinson equation of state as explained in the text.

conditions to the corresponding oxides. An example of this is the preparation of CeO_2 particles in the 2-nm size range by reaction of Ce metal with 2-methoxy ethanol (previously purged with N_2 to remove dissolved oxygen) [*9]. The conditions were: $T = 200\text{--}250^\circ\text{C}$, $t = 2$ h. Under these conditions, the authors obtained mostly a yellow solid that was CeO_2 with large particle sizes (~ 100 nm). In addition, they obtained a brown solution containing the 2-nm CeO_2 particles. These could be salted out of the solution using NaCl. Interestingly, the particles could be redispersed in water to give clear solutions that exhibit Beer–Lambert concentration dependence in optical absorption spectra. The authors suggest that these are the smallest ceria particles reported so far.

A combination of oxidation and hydrolysis under hydrothermal conditions has been used to prepare 10-nm spinel ZnGa_2O_4 particles [10]. The starting materials were Zn powder (in 10–20% excess) and GaCl_3 . The conditions were: $T = 150^\circ\text{C}$; $t = 10$ h. The authors suggest that dissolution of Zn raises the pH thereby assisting in the hydrolysis of Ga^{III} . The temperature, initial pH of the GaCl_3 solution and the Zn/Ga ratio affected the yield, purity and particle size of the product. At temperatures less than 130°C , the reaction was incomplete. At temperatures greater than 180°C , the particle sizes were large. When the starting pH of GaCl_3 was 3 or more, Ga_2O_3 formed as an impurity. When the Zn/Ga ratio was 1:2, the reaction was incomplete; an excess of Zn was found to be important. Excess ZnCl_2 formed could be washed away from the final product.

3.2. Routes involving hydrolysis

Hydrolytic routes are popular for the preparation of oxide nanoparticles. In aqueous solutions, a trivalent ion such as Fe^{III} is expected to be solvated by a shell of water molecules. One might therefore write the hydrolysis as:

This scheme indicates the necessity to raise the pH in the hydrolytic reaction, in order to remove protons that are generated and thereby to drive the reaction to the right. A popular hydrolytic route to oxides is the (acid or base-catalyzed) polycondensation of alkoxy compounds. This is particularly useful for compounds with quadrivalent ions, such as Si^{IV} , Ti^{IV} , Zr^{IV} , etc. For example, starting with titanium tetra-isopropoxide $\text{Ti}(\text{OR})_4$, one can write the acid or base-catalyzed hydrolysis as:

In detailed and very elegant work, Chemseddine and Moritz [**11] have described the preparation of sub-100 nm anatase nanoparticles of different sizes and also shapes. Their procedure involves a combination of hydrolysis and polycondensation of $\text{Ti}(\text{OR})_4$ in the presence of tetramethyl ammonium hydroxide, with a preliminary heat treatment under reflux, and final heat treatments ($T = 175\text{--}200^\circ\text{C}$, $t = 5$ h) being carried out in a Ti autoclave. The monodispersity of the anatase nanoparticles was sufficiently high that the authors were able to form nanocrystal superlattices and have presented not only TEM images in support of the formation of such superlattices, but also, low-angle powder X-ray diffraction data showing superlattice reflections.

Yanqing et al. [12] have hydrolyzed aqueous solutions of TiCl_4 hydrothermally ($T = 100\text{--}300^\circ\text{C}$ for different durations varying from 6 to 44 h). The size, morphology and phase of the resultant TiO_2 particles could be controlled. The amount of rutile increased with time, temperature and the initial TiCl_4 concentration. Small particle sizes were found when the initial TiCl_4 concentration was low and the reaction times were kept short.

TiO_2 (anatase and rutile) nanoparticles have been prepared starting from stabilized TiCl_4 solutions by Yin et al. [13] The procedure for the anatase nanoparticles involved hydrothermal treatment ($T = 220^\circ\text{C}$, $t = 2$ and 4 h) in the presence of citric acid. After 2 h, 4-nm particles were formed and after 4 h, 6-nm particles were formed. When a similar procedure was carried out but in the absence of citric acid, fibrous rutile was obtained. The particles obtained were smaller and more monodisperse than those which could be obtained through sol–gel processing. This is because the reaction, according to the authors, involves polycondensation of the anionic species $[\text{Ti}(\text{OH})_x(\text{citrate})_y\text{Cl}_z]^{n-}$.

Sun and coworkers [14] have prepared 3–5 nm ZrO_2

nanoparticles starting with $\text{Zr}(\text{OR})_4$ ($\text{R} = n\text{-propyl}$), ethanol, diethylene glycol and water. In different experiments, ammonia and HCl were also used. The solvothermal treatment conditions were $T = 190\text{--}230^\circ\text{C}$, $t = 24$ h. In the absence of glycol, the tetragonal phase is obtained. When glycol is used, cubic ZrO_2 nanoparticles could be obtained. Optimal starting ratios were 85:1 for ethanol/Zr; 20:1 for diethyleneglycol/Zr and 0.002 for HCl/Zr. Under these conditions, well-separated, small particles were obtained. The mechanism proposed is that the glycol coordinates with the Zr ion and the polycondensation of this species is sterically hindered so that the particle growth is limited.

Hirano [15] has described the preparation of spinel ZnGa_2O_4 nanoparticles starting with Zn and Ga sulphates with NH_3 added to adjust the pH to different values (initial pH varied from 2.5 through 10). The reactants were then treated hydrothermally at $T = 150\text{--}240^\circ\text{C}$, $t = 5\text{--}50$ h. An approximately 50% excess Zn^{II} was found to be necessary. Particle size increased with starting pH, and based on different parameters including T , could be varied from 5 to 25 nm.

Wu et al. [16] have demonstrated that microemulsion techniques of material containment can be combined with solvothermal routes to prepare rutile and anatase TiO_2 nanoparticles. These authors took a water-in-oil (cyclohexane) microemulsion using Triton X-100 and $n\text{-hexanol}$ as emulsifiers. The aqueous phase had dilute HCl or dilute HNO_3 , with $\text{Ti}(\text{OR})_4$ ($\text{R} = n\text{-butyl}$) as the reactant. The treatment conditions used were $T = 120\text{--}200^\circ\text{C}$, $t = 12\text{--}144$ h. The product phase and morphology could be controlled by the starting HCl or HNO_3 concentrations. When the HCl concentrations were high, rutile nanorods were produced. When 0.5 M HNO_3 was used, anatase nanoparticles were obtained. Typical anatase particle sizes were 50 nm. High reaction times and temperatures favor rutile formation. These authors have recorded TEM images of the microemulsions before hydrothermal treatment and see that the emulsions have the shapes of the products they form on heat-treatment.

3.3. Route involving thermolysis

In our laboratory, we have prepared a number of transition metal oxide nanoparticles containing either a single metal atom or two metal atoms (spinel oxides) using a thermolytic route involving the decomposition of cupferron complexes of transition metal ions in solvothermal toluene [*17]. This route is an extension of the one presented by Rockenberger et al. [4], who have used trioctyl amine as the solvent for the decomposition of cupferron complexes. Cupferron is $N\text{-phenyl}$, $N\text{-nitroso}$ hydroxylamine. A typical cupferron complex of a divalent metal ion M^{2+} is shown in Fig. 2. The crystal structure displayed is that of $\text{Cu}(\text{cupferron})_2$ with the coordinates taken from Ref. [18]. The complex is bonded to the metal atom through O and heating results in the decomposition

Fig. 2. Crystal structure of a typical cupferron complex. This one is of $\text{Cu}(\text{cupferron})_2$, with the large grey spheres representing the metal, and the organic ligand chelating to the metal through the small grey spheres which are oxygen. Such complexes are precursors for the thermolytic preparation of a large number of oxide nanoparticles.

of the complex to metal oxide with volatile by-products such as nitrosobenzene being produced.

In [*17], we have shown that magnetic sub-10 nm $\gamma\text{-Fe}_2\text{O}_3$ nanoparticles as well as magnetic spinel nanoparticles such as CoFe_2O_4 can be prepared by starting with the corresponding cupferron complexes and heating them solvothermally in toluene in the presence of an amine ($n\text{-octylamine}$ or $n\text{-dodecylamine}$) capping agent. The nanoparticles so produced are superparamagnetic. Dispersion can be controlled so that as-prepared nanoparticles show particle size distributions with widths of about 20%. To our knowledge, this is the only example of capped oxide nanoparticles being produced using a solvothermal technique. Fig. 3 displays the TEM image of octylamine-capped 7-nm CoFe_2O_4 spinel nanoparticles. This is only one of many mixed transition metal oxides that can be made using this route.

4. Chalcogenide nanoparticles

An important landmark preparation, actually of a pnictide InAs [19], has led the way to the preparation of a number of different chalcogenide nanoparticles using solvothermal routes. Much of the work comes from the group of Yi-Tai Qian in Hefei, China, and has been reviewed previously [**20]. In the InAs preparation [19],

Fig. 3. TEM image of 7-nm *n*-octylamine-capped CoFe_2O_4 nanoparticles prepared by the solvothermal decomposition of cupferron complexes in toluene. The bar is 20 nm. Reproduced with permission from The Royal Society of Chemistry [*17].

the authors took InCl_3 , AsCl_3 and Zn powder in xylene, and treated the reactants solvothermally at $T = 150^\circ\text{C}$, $t = 48$ h. The product was 15-nm InAs nanoparticles. The reaction takes place between the freshly formed elements that are obtained on the reduction of the In and As halides by Zn. Generally, water would be avoided in such a reaction. Here, trace quantities are actually beneficial for product formation. The suggested reaction is

4.1. Reactions starting from the elements

ZnSe nanoparticles (12–16 nm) have been prepared [21] by reacting the elements in pyridine ($T = 180^\circ\text{C}$, $t = 8$ h). The TEM images show platelets of aggregated particles, along with individual spherical particles. The cubic zinc blende structure was obtained under these conditions. The reaction could not be carried out in benzene; and in ethylenediamine, a complex was obtained. A similar

reaction with Zn and S gives different particles sizes depending on the time of heat treatment: 3 nm ($t = 5$ h), 10 nm ($t = 10$ h) 18 nm ($t = 24$ h). The particles were spherical. In reactions such as these, it is possible that the amine solvent solvates electrons that are given up by the metal. These electrons reduce the chalcogen to the anion resulting in precipitation.

ZnSe and CdSe particles (70–100 nm) have been prepared [*22] by Peng et al. from the elements under hydrothermal conditions ($T = 180^\circ\text{C}$, $t = 24$ h). This is an important reaction since water is the ideal solvent from most viewpoints. Were means to be found to reduce the particle size to the sub-10 nm range, this procedure has great potential for scale up. The cubic zinc blende structures were obtained from these reactions. At temperatures less than 180°C , the metal oxide or hydroxide and Se were obtained. This is perhaps to do with poor Se solubility below 180°C .

Qian and coworkers [23] have reported wurtzite ZnSe nanoparticles with sizes in the 18-nm range starting from the elements in ethylenediamine ($T = 120^\circ\text{C}$, $t = 6$ h). This reaction yields a complex with the formula $\text{ZnSe}(\text{en})$ where en is ethylenediamine. They have characterized this complex by X-ray diffraction and infrared spectroscopy. The complex on further treatment with dil. HCl gave large lamellar wurtzite ZnSe particles. It is important to keep the HCl concentration low to avoid dissolving ZnSe. The complex could also be decomposed by heating to 300°C in an argon atmosphere to obtain spherical 18-nm ZnSe particles.

4.2. Redox reactions and precipitations

CdS nanoparticles with different sizes and morphologies have been reported by Qian and coworkers [24] starting from the metal nitrates or sulphates, using thiourea as the S source. The solvents tried were water, ethanol, butanol, ethylene glycol, tetrahydrofuran (THF) or ethylenediamine. The smallest particles (6 nm) were obtained using ethylene glycol as the solvent ($T = 180^\circ\text{C}$, $t = 12$ h). In the amine solvents, rods were obtained, instead of spherical particles.

Our own contribution to the area is the preparation of thiol-capped 3-nm CdSe nanoparticles that are easily redissolved in non-polar solvents [*25]. We use toluene as the solvent. The reactants are cadmium stearate and Se powder. Following older work on the preparation of complex selenides [26], we have added tetralin (tetrahydronaphthalene) as a reducing agent. Tetralin is aromatized to naphthalene in the presence of Se, producing H_2Se in the process. This reacts with cadmium stearate to give CdSe. The process is inexpensive and relatively safe, and yields surprisingly monodisperse quantum dots (the particle size distributions have a width that is about 5% of the mean) with good luminescence properties. Fig. 4 displays the TEM image of dodecanethiol-capped 3-nm CdSe

Fig. 4. TEM image of 3-nm dodecanethiol-capped CdSe nanoparticles prepared by the solvothermal reaction of cadmium stearate in toluene. The bar is 50 nm. Reproduced with permission from The Royal Society of Chemistry [*25].

nanoparticles prepared solvothermally in toluene as described. To the best of our knowledge, this is the only report so far of a solvothermal route to surfactant-capped semiconductor chalcogenide nanoparticles.

Cu_{2-x}Se particles (18 nm) were obtained by Qian and coworkers [27] starting from CuI, Se, and ethylenediamine, with $T = 90^\circ\text{C}$, $t = 4$ h. The particles are spherical and quite monodisperse; 6-nm Co_9S_8 particles were prepared by Qian and coworkers [28] starting from the acetate $\text{Co}(\text{CH}_3\text{COO})_2$, hydrazine and thiourea in water, $T = 170^\circ\text{C}$, $t = 12$ h. Hydrazine plays an essential role here as a reducing agent, and in its absence, CoS was formed. A slight excess of Co was required to obtain near-stoichiometric materials. Particle sizes were estimated from X-ray diffraction line-broadening. At temperatures less than 160°C , the product was contaminated with CoS.

SnSe particles (45 nm) could be obtained [29] starting from SnCl_2 , Se and Na as a reducing agent in ethylenediamine with $T = 130^\circ\text{C}$, $t = 5$ h. A slight excess of Na was required. The particles were spherical and quite monodisperse. Higher temperatures and longer reaction times lead to agglomeration and larger particles. It has been suggested that Sn^{2+} is chelated by ethylenediamine. In benzene, toluene or tetrahydrofuran, the reaction is incomplete; 25-nm Bi_2Se_3 particles [30] could similarly be made starting from BiCl_3 and Se but using NaI as the reducing agent in ethylenediamine. The conditions were $T = 130^\circ\text{C}$, $t = 4$ h.

In_2S_3 nanoparticles have been reported by Xiong and coworkers [31] starting from $\text{InCl}_3 \cdot 4\text{H}_2\text{O}$, $\text{Na}_2\text{S}_2\text{O}_3 \cdot 5\text{H}_2\text{O}$

and ethanol. The conditions were $T = 180^\circ\text{C}$, $t = 24$ h. The reaction was also carried out in the presence of the surfactant CTAB (cetyl trimethylammonium bromide). The concentrations of the starting materials were found to influence the size and morphology of the particles. At low concentrations, 15-nm nanoparticles were obtained. When the concentration was increased, nanowhiskers and nanorods were obtained. CTAB reduced the particle size and led to narrower particle size distributions. The solvent itself undergoes oxidation leading to the reduction of In^{3+} . The proposed reaction is

Qian and coworkers [32] have prepared MSe_2 particles with $\text{M} = \text{Ni}$, Co and Fe from the reaction of MCl_2 with a mixture of hydrazine and Se in alkaline conditions, solvothermally, using as solvents H_2O , N,N -dimethylformamide (DMF), pyridine, acetylacetone or ethylenediamine. Typical conditions involve $T = 80$ – 200°C , $t = 12$ – 48 h. Control over particle size and shape could be achieved through changing the solvent, temperature and reaction time. For example, using DMF, spherical particles could be prepared. With pyridine at low temperatures, filaments were obtained. Hydrazine is necessary in order to reduce the chalcogen to the ion under alkaline conditions. Neither CoSe_2 nor FeSe_2 crystallize in the cubic pyrites phase but instead form orthorhombic compounds. NiSe_2 however crystallizes in the usual cubic phase. The reactions are incomplete in water and acetylacetone, perhaps due to the lower solubility of Se in these solvents. In ethylenediamine, a complex is obtained instead of the chalcogenide.

Chen and Fan [*33] have prepared MS_2 and MSe_2 particles ($\text{M} = \text{Fe}$, Co, Ni, Mo) with sizes ranging from 4 to 200 nm under hydrothermal conditions. They start with MCl_2 (when $\text{M} = \text{Ni}$, Co or Fe) and sodium thiosulphate $\text{Na}_2\text{S}_2\text{O}_3$ or sodium selenosulphate Na_2SSeO_3 . The hydrothermal conditions are $T = 140$ – 150°C , $t = 12$ h. Sodium selenosulphate is easily prepared by boiling an aqueous solution of sodium sulphite Na_2SO_3 with Se powder for 10 h. All the dichalcogenides of Fe, Co and Ni were cubic. The pH of the starting solution was found to influence the reaction. For $\text{pH} > 7$ in the NiS_2 preparation, $\text{Ni}(\text{OH})_2$ was the product. When the $\text{pH} < 3$, NiS and Ni_3S_4 were the products. For the preparation of MoS_2 and MoSe_2 , the starting materials were Na_2MoO_4 , hydrazine (as a reducing agent) and $\text{Na}_2\text{S}_2\text{O}_3/\text{Na}_2\text{SSeO}_3$. The hydrothermal conditions were $T = 135^\circ\text{C}$, $t = 12$ h. Reported sizes were from X-ray Scherrer broadening as well as from transmission electron microscopy and these were found to be consistent. The important reaction suggested for ME_2

formation when M is Fe, Co, Ni is between the thiosulphate or selenosulphate ion and water according to:

where E is S or Se. The E^{2-} ion precipitates the metal chalcogenide. The authors provide as evidence, the detection of SO_4^{2-} and H^+ in the reaction products. In the MoS_2 case, even though sodium thiosulphate is a good reducing agent, hydrazine was needed for the reduction. MoS_2 was formed in this reaction when the pH range was kept between 7 and 14. When the pH was less than 5, molybdenum bronzes were formed.

Qian and coworkers [34] report the solvothermal preparation of the important compound semiconductor CuInSe_2 . They obtain 15-nm particles starting from CuCl_2 , InCl_3 and Se. The solvent was either ethylenediamine or diethylamine, with $T = 180^\circ\text{C}$, 15 h when the solvent was ethylenediamine, and 36 h in the case of diethylamine. In ethylenediamine, whiskers were obtained. Spherical particles were obtained in diethylamine. The phase was chalcopyrite. The proposed reaction involves:

$\text{CuInSe}_{2-x}\text{S}_x$ [35] has been prepared by Qian and coworkers using InCl_3 , CuCl_2 , S and Se with ethylenediamine as the solvent ($T = 180^\circ\text{C}$, $t = 15$ h). Diethylamine can also be used but longer times are required ($t = 48$ h). The average particle size was 15 nm.

AgGaS_2 (5–7 nm) and 9–12 nm AgInS_2 nanoparticles have been prepared [36] in a reaction involving AgCl , the metal (Ga or In) and S in ethylenediamine ($T = 180$ – 230°C , $t = 10$ h). Here, the solvent plays a dual role of dissolving S as well as complexing Ag^+ . The particles were spherical but agglomerated. The reaction cannot be carried out in pyridine or benzene. The suggested mechanism is:

CuMS_2 (M=In and Ga) nanoparticles with sizes of the order of 10 nm (M=In) and of the order of 35 nm (M=Ga) have been similarly prepared by the reaction of CuCl , M and excess S in water [37] at $T = 200^\circ\text{C}$ and $t = 12$ h. When the solvent was pyridine instead of water, larger particles were obtained. When ethylenediamine was used as the solvent, the particle shapes were irregular. The proposed mechanism is that S disproportionates to S^{2-} and an unspecified oxidized species with S. The latter oxidizes the metal and the sulphide is precipitated. The reaction is like the one for the Ag compounds presented earlier:

The products AgGaS_2 and AgInS_2 are both tetragonal chalcopyrites. In these reactions, the M (Ga or In) melts and the reaction takes place through a liquid-solution diffusion process.

Using a combination of microemulsions and solvothermal techniques, Gan et al. [38] have prepared 12-nm Mn-doped ZnS nanoparticles. The microemulsions comprised petroleum ether as the oil, NP5 or NP9 surfactants, [these are poly(oxoethylene)₅ nonylphenoether, or poly(oxoethylene)₉ nonylphenoether] and water. To one part of the emulsion, Na_2S was added and to the other, MCl_2 added (M=Zn and Mn). These were mixed and treated solvothermally ($T = 120^\circ\text{C}$, $t = 15$ h). Mn content was 0.8 mol% in the product. The particles were spherical but with a wide size distribution. Photoluminescence intensities of the samples were enhanced by a factor of 60 compared to the sample prepared by a conventional aqueous reaction at room temperature. This is attributed to the surface passivation of the Mn-doped ZnS nanocrystals and the formation of the cubic zinc blende structure.

5. New developments in solvothermal preparations

We mention here two relatively new techniques in solvothermal/hydrothermal chemistry that have, amongst other things, been employed for the preparation of oxide nanoparticles. We believe these to be important for possible scale-up of solvothermal routes to nanoparticles. The two techniques are: (i) microwave-solvothermal reactions and (ii) flow-solvothermal reactions.

Microwave-hydrothermal techniques employ polymeric bombs/autoclaves that are transparent to microwaves but whose aqueous contents couple and rapidly heat up to (provided the system is controlled) a temperature that is in turn governed by the pressure. Systems are commercially available for so-called microwave-hydrothermal digestion of analytes for analytical chemistry. These have been put to use by Komarneni and coworkers [39] to prepare a number of different oxide nanoparticles. For example, they have prepared 5–20 nm MnFe_2O_4 , CoFe_2O_4 , NiFe_2O_4 and ZnFe_2O_4 ferrite particles. In a typical procedure, metal nitrates are treated with NH_3 till a specific pH is reached. These are then subjected to digestion in the microwave hydrothermal assembly ($T = 164$ – 194°C , $t \sim 4$ min). The remarkably small reaction times are worthy of note. In addition, as in any microwave heating process, the energy is not wasted since it is dumped to the solvent, not the bomb.

In flow-hydrothermal techniques, a preheated solvent is mixed with reactants just before introducing the mixture into a heated chamber whose pressure is controlled using a back-pressure regulator. The individual components can be constructed with Swagelok™ fittings. An essential feature is the pumping of the reactants using high-pressure pumps of the kind employed in high-performance liquid chroma-

Fig. 5. Scheme of the flow-hydrothermal system used in Ref. [**40] for the preparation of oxide nanoparticles in a continuous process. The pumps P, mix the preheated solvent and reactants and these are introduced into a chamber that is heated to the desired temperature. The system pressure is controlled by the back-pressure regulator (BPR). Adapted from Ref. [**40] with permission from the Royal Society of Chemistry.

tography (HPLC). Cabañas et al. [**40] have described the preparation of nanoparticulate $\text{CeO}_2\text{--ZrO}_2$ solid solutions using a system such as the one described. Mixed ceric ammonium nitrate and zirconium acetate solutions were added to preheated water at 400 °C. The mixing point temperature then dropped to 300 °C at the flow rates used. A residence time of 9 s at a (regulated) pressure of 25 MPa was sufficient to yield the product, which comprised nanoparticles with sizes as small as 4 nm. Fig. 5 displays a schematic of the flow-solvothermal system used by these authors.

A criterion that helps in the preparation of monodisperse nanoparticles is the requirement that nucleation of the particles take place rapidly, and this is followed by a well-separated growth phase. During the growth phase, there should be no new nuclei formed. The reason is that if nuclei keep forming during the growth stage, the initially formed nuclei will grow into large nanoparticles while the nuclei formed at later stages will not grow very much. Both the new techniques listed here show great promise, not only for scale-up, but also for monodisperse nanoparticles, given that the microwave solvothermal technique involves rapid heating and that the flow-solvothermal technique involves short contact times.

Acknowledgements

We thank the Department of Science and Technology for their support of this work, and Dr M. Giridhar for discussions.

References

Papers of particular interest, published within the annual period of review, have been highlighted as:

* of special interest;

** of outstanding interest.

- [1] Murray CB, Norris DJ, Bawendi MG. Synthesis and characterization of nearly monodisperse CdE (E=S, Se, Te) semiconductor nanocrystallites. *J Am Chem Soc* 1993;115:8706–15.
- [2] Trentler TJ, Denler TE, Bertone JF, Agrawal A, Colvin VL. Synthesis of TiO_2 nanocrystals by nonhydrolytic solution-based reactions. *J Am Chem Soc* 1999;121:1613–4.
- [3] Green M, O'Brien P. A simple one phase preparation of organically capped gold nanocrystals. *J Chem Soc Chem Commun* 2000:183–84.
- [4] Rockenberger J, Scher EC, Alivisatos AP. A new non-hydrolytic single-precursor approach to surfactant-capped nanocrystals of transition metal oxides. *J Am Chem Soc* 1999;121:11595–6.
- [5] Klinowski J, Barrie PJ, editors. Recent advances in zeolite science, Amsterdam: Elsevier, 1990.
- [6] Yu SH. Hydrothermal/solvothermal processing of advanced ceramic materials. *J Ceram Soc Jpn* 2001;109:S65–75.
- [7] Smith JM, van Ness HC, Abbott MM. Introduction to chemical engineering thermodynamics, 6th edition. Singapore: McGraw-Hill, 2001.
- [8] Reid RC, Prausnitz JM, Poling BE. The properties of liquids and gases, 4th edition. Singapore: McGraw-Hill, 1986.
- [9] Inoue M, Kimura M, Inui T. Transparent colloidal solution of 2 nm ceria particles. *J Chem Soc Chem Commun* 1999:957–58.
- [10] Li Y, Duan X, Liao H, Qian Y. Self-regulation synthesis of nanocrystalline ZnGa_2O_4 by hydrothermal reaction. *Chem Mater* 1998;10:17–8.
- [**11] Chemseddine A, Moritz T. Nanostructuring titania: Control over nanocrystal structure, size, shape, and organization. *Eur J Inorg Chem* 1999:235–45.
- [12] Yanqing Z, Erwei S, Zhizhan C, Wenjun L, Xingfang H. Influence of solution concentration on the hydrothermal preparation of titania crystallites. *J Mater Chem* 2001;11:1547–51.
- [13] Yin H, Wada Y, Kitamura T, Sumida T, Hasegawa Y, Yanagida S. Novel synthesis of phase-pure nano-particulate anatase and rutile TiO_2 using TiCl_4 aqueous solutions. *J Mater Chem* 2002;12:378–83.
- [14] Zhao J, Fan W, Wu D, Sun Y. Stable nanocrystalline zirconia sols prepared by a novel method; alcohol thermal synthesis. *J Mater Res* 2000;15:402–6.
- [15] Hirano M. Hydrothermal synthesis and characterization of ZnGa_2O_4 spinel fine particles. *J Mater Chem* 2000;10:469–72.
- [16] Wu M, Long J, Huang A, Luo Y, Feng S, Xu R. Microemulsion-mediated hydrothermal synthesis and characterization of nanosized rutile and anatase particles. *Langmuir* 1999;15:8822–5.
- [*17] Thimmaiah S, Rajamathi M, Singh N, Bera P, Meldrum FC, Chandrasekhar N, Seshadri R. A solvothermal route to capped nanoparticles of $\gamma\text{-Fe}_2\text{O}_3$ and CoFe_2O_4 . *J Mater Chem* 2001;11:3215–21.
- [18] Elerman Y, Atakol O, Svoboda I, Geselle M. Bis(cupferronato)copper(II), $[\text{Cu}(\text{C}_6\text{H}_5\text{N}_2\text{O}_2)_2]$. *Acta Crystallogr* 1995;C51:1520–2.
- [19] Li YD, Duan XF, Qian YT, Yang L, Ji MR, Li CW. Solvothermal co-reduction route to the nanocrystalline III–V semiconductor InAs. *J Am Chem Soc* 1997;119:7869–70.
- [**20] Qian Y. Solvothermal synthesis of nanocrystalline III–V semiconductors. *Adv Mater* 1999;11:1101–2.
- [21] Li Y, Ding Y, Qian Y, Zhang Y, Yang L. A solvothermal elemental reaction to produce nanocrystalline ZnSe. *Inorg Chem* 1998;37:2844–5.
- [*22] Peng Q, Dong Y, Deng Z, Sun X, Li Y. Low-temperature elemental-direct-reaction route to II–VI semiconductor nanocrystalline ZnSe and CdSe. *Inorg Chem* 2001;40:3840–1.
- [23] Zhan JH, Yang XG, Zhang WX, Wang DW, Xie Y, Qian YT. A solvothermal route to wurtzite ZnSe nanoparticles. *J Mater Res* 2000;15:629–32.
- [24] Yu SH, Yang J, Han ZH, Zhou Y, Yang RY, Qian YT, Zhang YH. Controllable synthesis of nanocrystalline CdS with different morphologies and particle sizes by a novel solvothermal process. *J Mater Chem* 1999;9:1283–7.

- [*25] Gautam UK, Rajamathi M, Meldrum F, Morgan P, Seshadri R. A solvothermal route to capped CdSe nanoparticles. *J Chem Soc Chem Commun* 2001;629–30.
- [26] Mitchell PWD, Morgan PED. Direct precipitation method for complex crystalline chalcogenides. *J Am Ceram Soc* 1974;57:278.
- [27] Wang W, Yan P, Liu F, Xie Y, Geng Y, Qian Y. Preparation and characterization of nanocrystalline Cu_{2-x}Se by a novel solvothermal pathway. *J Mater Chem* 1998;8:2321–2.
- [28] Zhan JH, Yang XG, Xie Y, Wang DW, Qian YT, Liu XM. Hydrazine-controlled hydrothermal synthesis of Co_9S_8 from a homogeneous solution. *J Mater Res* 1999;14:4418–20.
- [29] Wang W, Geng Y, Qian Y, Wang C, Liu X. A convenient, low temperature route to nanocrystalline SnSe. *Mater Res Bull* 1999;34:403–6.
- [30] Wang W, Geng Y, Qian Y, Xie Y, Liu X. Synthesis and characterization of nanocrystalline Bi_2Se_3 by solvothermal method. *Mater Res Bull* 1999;34:131–4.
- [31] Xiong Y, Xie Y, Du G, Tian X. A solvent-reduction and surface-modification technique to morphology control of tetragonal In_2S_3 nanocrystals. *J Mater Chem* 2002;12:98–102.
- [32] Yang J, Cheng GH, Zeng JH, Yu SH, Liu XM, Qian YT. Shape-control and characterization of transition metal diselenides MSe_2 ($\text{M}=\text{Ni}, \text{Co}, \text{Fe}$) prepared by a solvothermal-reduction process. *Chem Mater* 2001;13:848–53.
- [*33] Chen X, Fan R. Low-temperature hydrothermal synthesis of transition metal dichalcogenides. *Chem Mater* 2001;13:802–5.
- [34] Li B, Xie Y, Huang H, Qian Y. Synthesis by a solvothermal route and characterization of CuInSe_2 nanowhiskers and nanoparticles. *Adv Mater* 1999;11:1456–9.
- [35] Xiao J, Xie Y, Xiong Y, Tang R, Qian Y. A mild solvothermal route to chalcopyrite quaternary semiconductor $\text{CuIn}(\text{Se}_x\text{S}_{1-x})_2$ nanocrystallites. *J Mater Chem* 2001;11:1417–20.
- [36] Hu J, Lu Q, Tang K, Qian Y, Zhou G, Liu X. Solvothermal reaction route to nanocrystalline semiconductors AgMS_2 ($\text{M}=\text{Ga}, \text{In}$). *J Chem Soc Chem Commun* 1999:1093–94.
- [37] Lu Q, Hu J, Tang K, Qian Y, Zhou G, Liu X. Synthesis of nanocrystalline CuMS_2 ($\text{M}=\text{In}, \text{Ga}$) through a solvothermal process. *Inorg Chem* 2000;39:1606–7.
- [38] Gan LM, Liu B, Chew CH, Xu SJ, Chua SJ, Loy GL, Xu GQ. Enhanced photoluminescence and characterization of Mn-doped ZnS nanocrystallites synthesized in microemulsion. *Langmuir* 1997;13:6427–31.
- [**39] Komarneni S, D'Arigo MC, Leonelli C, Pellacani GC, Katsuki H. Microwave-hydrothermal synthesis of nanophase ferrites. *J Am Ceram Soc* 1998;81:3041–3.
- [**40] Cabañas A, Darr JA, Lester E, Poliakov M. A continuous and clean one-step synthesis of nano-particulate $\text{Ce}_{1-x}\text{Zr}_x\text{O}_2$ solid solutions in near-critical water. *J Chem Soc Chem Commun* 2000;901–2; Cabañas A, Darr JA, Lester E, Poliakov M. Continuous hydrothermal synthesis of inorganic materials in a near-critical water flow reactor; the one-step synthesis of nanoparticulate $\text{Ce}_{1-x}\text{Zr}_x\text{O}_2$ ($x=0, 1$) solid solutions. *J Mater Chem* 2001;11:561–8.