Low temperature synthesis of layered Na_xCoO_2 and K_xCoO_2 from NaOH/KOH fluxes and their ion exchange properties[†]

C SHIVAKUMARA and M S HEGDE*

Solid State and Structural Chemistry Unit, Indian Institute of Science,
Bangalore 560 012, India
e-mail: mshegde@sscu.iisc.ernet.in

Abstract. We report a low temperature synthesis of layered $\text{Na}_{0.20}\text{CoO}_2$ and $\text{K}_{0.44}\text{CoO}_2$ phases from NaOH and KOH fluxes at 400°C. These layered oxides are employed to prepare hexagonal HCoO_2 , Li_xCoO_2 and Delafossite AgCoO_2 phases by ion exchange method. The resulting oxides were characterised by powder X-ray diffraction, X-ray photoelectron spectroscopy, SEM and EDX analysis. Final compositions of all these oxides are obtained from chemical analysis of elements present. $\text{Na}_{0.20}\text{CoO}_2$ oxide exhibits insulating to metal like behaviour, whereas AgCoO_2 is semiconducting.

Keywords. Layered oxides; ion exchange reaction; powder X-ray diffraction; NaOH and KOH fluxes.

1. Introduction

Layered oxides have interesting chemical and physical properties. They often allow the reversible insertion and extraction of cations or protons. They are used as electrodes in rechargeable batteries. Na_xCoO_2 and K_xCoO_2 layered oxides crystallizing in a variety of structure types and varied amount of Na or K ions are the precursors to Li_xCoO_2 , which is a cathode material for Li ion batteries. Na_xCoO_2 ($x \leq 1$) was first prepared by Fouassier *et al.*¹ by heating stoichiometric amounts of Co_3O_4 and Na_2O_2 . Na_xCoO_2 was also prepared by heating stoichiometric amounts of NaOH and Co metal. Alternatively, heating Co metal in Na_2CO_3 at 850°C also gave Na_xCoO_2 phases. Balsys and Davis² have refined the structure of $\text{Na}_{0.7}\text{CoO}_2$ using neutron diffraction data. The structure of Na_xCoO_2 consists of sheets of edge-sharing CoO_6 octahedra between which sodium ions are intercalated within a trigonal prismatic or octahedral coordination. The structural change accompanied by ion-exchange is reported in $\text{Na}_{0.7}\text{CoO}_2$ by Delmas *et al.*³ In $\text{Na}_{0.7}\text{CoO}_2$ the anion sequence is ABBA. When these material is ion-exchanged with LiCl, a metastable form of LiCoO_2 with the layer sequence ABCBA is obtained. Recently, Takada *et al.*⁴ reported superconductivity in $\text{Na}_x\text{CoO}_2 \cdot y\text{H}_2\text{O}$ ($x \approx 0.35$, $y \approx 1.3$) with a T_c of about 5 K. There is a marked resemblance in superconducting properties between the $\text{Na}_x\text{CoO}_2 \cdot y\text{H}_2\text{O}$ and high T_c copper oxides, suggesting that the two systems have similar underlying physics. Inorganic solids exchanged with protons to give rise to new $\text{HTaWO}_6 \cdot \text{H}_2\text{O}$ phases has been reported by Groult *et al.*⁵ The conversion of LiNbO_3 and LiTaO_3 to HNbO_3 and HTaO_3 respectively, is done by the treatment with hot aqueous acid.⁶ The exchange of

[†]Dedicated to Professor C N R Rao on his 70th birthday

*For correspondence

Li^+ by protons is accompanied by a topotactic transformation of the rhombohedral LiNbO_3 structure to the cubic perovskite structure of HNbO_3 . Bhat and Gopalakrishnan⁷ have synthesized novel protonated layered oxides, $\text{HMWO}_6 \cdot 1.5\text{H}_2\text{O}$ ($\text{M} = \text{Nb}$ or Ta) by topotactic exchange of lithium in trirutile LiMWO_6 with protons by treatment with dilute HNO_3 . Electrocatalytic activities of HCoO_2 for the oxidation of hydrogen in solid oxide fuel cell has been studied,⁸ and it was found to be an efficient anode material for the oxidation of hydrogen with the oxygen transported through the solid electrolyte.

$\text{K}_{0.5}\text{CoO}_2$ was prepared by heating stoichiometric amounts of KOH and Co_3O_4 in O_2 at 450°C . KCo_2O_4 ,⁹ $\text{KCo}_{0.5}\text{O}_2$, $\text{KCo}_{0.67}\text{O}_2$, **a** KCoO_2 and **b** KCoO_2 phases¹⁰ and also RbCo_2O_4 and CsCo_2O_4 have been identified.¹¹ The known Na_xCoO_2 and K_xCoO_2 phases and their structure are summarized in table 1.

We were interested in synthesizing layered Na_xCoO_2 and K_xCoO_2 by soft chemistry route employing NaOH and KOH fluxes. In these layered oxides, Co is present in +3 and +4 states. Delmas *et al*¹² have reported that the non-stoichiometric alkali metal cobalt oxides are metallic, while stoichiometric NaCoO_2 is a semiconducting. KCo_2O_4 ⁹ and NaCo_2O_4 ¹³ are metallic oxides.

NaI and KI could also be employed to grow Na_xCoO_2 and K_xCoO_2 phases. Here we report low temperature synthesis of layered Na_xCoO_2 and K_xCoO_2 phases from NaOH and KOH fluxes. These layered oxides are employed to make H_xCoO_2 , Li_xCoO_2 and also Ag_xCoO_2 by ion exchange method. We also report Na_xCoO_2 synthesised from molten NaI flux.

Table 1. Compositions, crystal structure and lattice parameters of known A_xCoO_2 and ACo_2O_4 ($\text{A} = \text{Na}, \text{K}, \text{Rb}$ and Cs) phases.

Compositions	Structure	Lattice parameters ($\text{\AA}$)			Reference
		<i>a</i>	<i>b</i>	<i>c</i>	
$\text{Na}_{0.82}\text{CoO}_2$	Orthorhombic, <i>P</i> 3	4.87	2.81	5.75	1
$\text{Na}_{0.90}\text{CoO}_2$	Orthorhombic, <i>P'</i> 3	4.54	2.83	5.79	1
$\text{Na}_{0.95}\text{CoO}_2$	Orthorhombic, <i>O'</i> 3	4.88	2.86	5.77	1
NaCoO_2	Orthorhombic, <i>O</i> 3	4.99	2.88	6.17	1
$\text{Na}_{0.90}\text{CoO}_2$	Hexagonal	2.88	—	15.58	1
a' $\text{-Na}_{0.75}\text{CoO}_2$	Monoclinic	4.89	2.87	5.77	1
$\text{Na}_{0.55}\text{CoO}_2$	Orthorhombic	2.83	4.84	16.53	1
$\text{Na}_{0.72}\text{CoO}_2$	Hexagonal	2.83	—	10.88	1
NaCoO_2	Hexagonal, <i>O</i> 3	2.88	—	15.58	1
$\text{Na}_{0.7}\text{CoO}_2$	Hexagonal, <i>P</i> 2	2.83	—	10.82	2
$\text{Na}_{0.53}\text{CoO}_2$	Hexagonal, <i>P</i> 2	2.84	—	10.81	1
$\text{Na}_{0.52}\text{CoO}_2$	Monoclinic, <i>P</i> 6	4.84	2.83	5.71	1
KCo_2O_4	Hexagonal	2.84	—	12.35	9
$\text{KCo}_{0.5}\text{O}_2$	Pseudohexagonal	2.83	—	18.46	10
$\text{KCo}_{0.67}\text{O}_2$	Hexagonal	2.83	—	12.26	10
a -KCoO_2	Tetragonal	5.37	—	7.87	10
b -KCoO_2	Tetragonal	5.71	—	7.29	10
$\text{K}_{0.5}\text{Co}_2\text{O}_4$	Hexagonal	2.84	—	12.26	10
RbCo_2O_4	Hexagonal	2.83	—	13.04	11
CsCo_2O_4	Hexagonal	2.84	—	13.98	11

2. Experimental

2.1 Synthesis of Na_xCoO_2 and K_xCoO_2

Layered Na_xCoO_2 and K_xCoO_2 phases were synthesized from cobalt oxalate or nitrate salts mixed with NaOH or KOH (AR grade) in the weight ratio of 1:10 in a recrystallized alumina crucible. For the preparation of Na_xCoO_2 , a typical run contains $\text{CoC}_2\text{O}_4 \cdot 2\text{H}_2\text{O}$ (3.6591 g) and NaOH (7.9798 g). The mixture was heated at 400°C for 12 h in a muffle furnace. Initially a clear blue solution was observed and gradually black flaky crystals precipitated. The furnace was put off after 12 h. Excess alkali was washed with distilled water and dried at 110°C . Similarly, K_xCoO_2 phase is synthesized from KOH flux.

NaI was also used as a flux to prepare Na_xCoO_2 phase. $\text{CoC}_2\text{O}_4 \cdot 2\text{H}_2\text{O}$ is mixed with 10 times excess of dry NaI in a recrystallized alumina crucible. The mixture was heated to 750°C for 24 h. The melt was furnace cooled and washed with hot distilled water until no Na^+ ion was detected in the filtrate. The black solid was filtered and dried at 110°C .

2.1a Preparation of H_xCoO_2 : Na_xCoO_2 and K_xCoO_2 phases are non-stoichiometric layered oxides. The ion exchange of sodium or potassium with proton was achieved by mixing 1 g of Na_xCoO_2 or K_xCoO_2 samples in 50 ml of 1 M HCl . The solution was kept for 12 h and the acid was decanted. This ion exchange treatment was repeated thrice for the same sample, each time in fresh 1 M HCl solution. The exchanged sample was washed with distilled water and dried at 110°C .

2.1b Preparation of Ag_xCoO_2 : Na_xCoO_2 or K_xCoO_2 precursor was mixed with two times excess of AgNO_3 . The mixture was heated at 275°C , above the mp of AgNO_3 (212°C) for 3 h. The melt was furnace cooled to room temperature, washed with distilled water until the filtrate was free from Na^+/Ag^+ ions. Finally, the resulting black flaky crystals were isolated and dried at 110°C .

2.1c Preparation of Li_xCoO_2 : Layered Li_xCoO_2 phase was also synthesized by cation exchange reaction. Na_xCoO_2 or K_xCoO_2 precursor is mixed with twice the excess of LiNO_3 and heated to 250°C for 3 h and cooled to room temperature. Excess LiNO_3 was washed with distilled water and dried at 110°C . Here also, black flaky crystals were isolated.

2.2 Characterisation

The flux-grown oxides were characterized by powder X-ray diffraction (XRD) using Siemens D5005 diffractometer with $\text{Cu K}\alpha$ ($1.5418 \text{ \AA}$) radiation. The morphology and composition of these crystalline phases were obtained from scanning electron microscopy (SEM), energy dispersive X-ray (EDX) analysis. Final composition of these phases was obtained by chemical analysis of the elements present. Oxygen content was determined by iodometric titration. Electrical resistivity measurements were done on the sintered pellets at 800°C using four-probe technique. X-ray photoelectron (XPS) study of selected phases were done using ESCA-3 Mark II spectrometer with $\text{Al K}\alpha$ radiation. There was no charging of the samples. Binding energy of the core levels are calibrated with reference to C (1s) at 285 eV.

2.2a Cobalt estimation: About 50 mg of the compound was dissolved in 10 ml of 6 M HCl and evaporated to dryness. The salt was dissolved in 25 ml of distilled H₂O. To this, 3 drops of xylenol orange indicator was added followed by very dilute sulphuric acid until the colour just changes from red to yellow. Then powdered hexamine was added with constant stirring until the deep red colour is restored (pH = 6). The solution was warmed to 40°C and titrated with standard 0.025 M EDTA solution.¹⁴ Accuracy of the cobalt estimation is confirmed to be better than 0.5%.

2.2b Sodium and potassium estimation: Sodium and potassium contents were estimated by flame photometry. About 50 mg of the compound was dissolved in 10 ml of 6 M HCl, evaporated to dryness, and redissolved in H₂O to 100 ml. Standard solutions were prepared from analytical grade NaCl and KCl salts dried at 200°C. Accuracy of estimation is better than 0.5%.

3. Results and discussion

The flux grown crystalline phases obtained from NaOH and subsequent ion exchanged oxides were analysed and their compositions are summarized in table 2. Accordingly, Na_{0.2}CoO₂ is obtained from NaOH flux and H_{0.96}Na_{0.04}CoO₂, Li_{0.29}CoO₂ and AgCoO₂ from ion exchange of Na_{0.2}CoO₂. The composition of KOH flux grown oxide is K_{0.44}CoO₂. Composition of the ion exchanged phases from K_{0.44}CoO₂ were H_{0.98}K_{0.02}CoO₂, Li_{0.42}CoO₂ and AgCoO₂.

Scanning electron microscopy (SEM) study shows that the morphology of the parent Na_{0.2}CoO₂ and K_{0.44}CoO₂ compounds is hexagonal. Ion exchanged H_{0.98}Na_{0.04}CoO₂, Li_{0.29}CoO₂ and AgCoO₂ phases also showed hexagonal morphology. Typical SEM images of the parent Na_{0.2}CoO₂ and those ion exchanged with H⁺, Li⁺ and Ag⁺ are given in figure 1a–d respectively. Na⁺, K⁺, Ag⁺ and Co ion concentrations obtained from EDX analysis were close to the chemical analysis.

Powder X-ray diffraction patterns of the parent Na_{0.2}CoO₂ and ion-exchanged phases are shown in figure 2a–d respectively. Similarly, XRD patterns of the K_{0.44}CoO₂ and

Table 2. Chemical analysis data, synthetic condition and lattice parameters of Na_xCoO₂ and K_xCoO₂ obtained from NaOH/NaI and KOH melts and H⁺, Li⁺ and Ag⁺ ion exchanged compounds.

Composition*	Synthetic condition	Structure	Lattice parameters (Å)	
			<i>a</i>	<i>c</i>
Na _{0.20} CoO ₂ (A)	400°C/12 h; NaOH	Hexagonal	2.873 (4)	20.646 (3)
H _{0.96} Na _{0.04} CoO ₂	A → RT/12 h; 1 M HCl	Hexagonal	2.860 (7)	13.158 (8)
Li _{0.29} CoO ₂	A → 275°C/3 h; LiNO ₃	Hexagonal	2.835 (4)	14.038 (4)
AgCoO ₂	A → 250°C/3 h; AgNO ₃	Hexagonal	2.859 (5)	36.644 (3)
Na _{0.27} CoO ₂	750°C/24 h; NaI	Orthorhombic	<i>a</i> = 2.83 (4) <i>b</i> = 4.84 (5)	16.52 (3)
K _{0.44} CoO ₂ (B)	400°C/12 h; KOH	Hexagonal	2.854 (4)	18.652 (3)
H _{0.98} K _{0.02} CoO ₂	B → RT/12 h; 1 M HCl	Hexagonal	2.676 (8)	13.167 (4)
Li _{0.42} CoO ₂	B → 275°C/3 h; LiNO ₃	Hexagonal	2.816 (4)	14.037 (5)
AgCoO ₂	B → 250°C/3 h; AgNO ₃	Hexagonal	2.861 (3)	36.648 (4)

*Analysis accurate within ± 0.005

Figure 1. Scanning electron micrographs of (a) $\text{Na}_{0.20}\text{CoO}_2$, (b) $\text{H}_{0.96}\text{Na}_{0.04}\text{CoO}_2$, (c) $\text{Li}_{0.29}\text{CoO}_2$ and (d) AgCoO_2 .

those ion exchanged with H^+ , Li^+ and Ag^+ are given in figure 3a–d respectively. All these patterns can be indexed in the hexagonal structure and the lattice parameters are summarized in table 2. Since the flux-grown compounds are large flaky crystals, even on fine grinding, powder X-ray patterns show large peaks due to the c -axis oriented (00l) reflections. However, expansion of small peaks at higher angles (2θ from 40 to 90°, not shown in the figures 2 and 3) gave peaks such as (104) and (015) reflections. Lattice parameters of $\text{Na}_{0.2}\text{CoO}_2$ is given in table 2. However, indexed powder X-ray pattern of AgCoO_2 phase given in figure 4 (data were collected at a scan rate of 1°/min), clearly shows large number of diffracted lines indexed in hexagonal structure with lattice parameters $a = 2.862(1) \text{ \AA}$, $c = 36.684(4) \text{ \AA}$. These parameters agree well with the reported AgCoO_2 phase¹⁵ (JCPDS 25-0761).

The compound synthesized from NaI flux has the composition $\text{Na}_{0.27}\text{CoO}_2$. In this preparation, there is no flaky type oriented crystals, unlike in the compound prepared from NaOH melt. The diffraction lines are indexed in the orthorhombic structure with lattice parameters $a = 2.83(4)$, $b = 4.84(5)$ and $c = 16.52(3)$ and the corresponding XRD pattern is given in figure 5. There are no diffraction lines assignable to impurity phases. Lattice parameters of $\text{Na}_{0.27}\text{CoO}_2$ compound obtained from NaI flux is close to $\text{Na}_{0.55}\text{CoO}_2$ orthorhombic phase.¹

Figure 2. Powder XRD patterns for (a) $\text{Na}_{0.20}\text{CoO}_2$, (b) $\text{H}_{0.96}\text{Na}_{0.04}\text{CoO}_2$, (c) $\text{Li}_{0.23}\text{CoO}_2$ and (d) AgCoO_2 .

The proton-exchanged compound from $\text{Na}_{0.2}\text{CoO}_2$ has the compositions $\text{H}_{0.96}\text{Na}_{0.04}\text{CoO}_2$ and $\text{H}_{0.98}\text{K}_{0.02}\text{CoO}_2$ from $\text{K}_{0.44}\text{CoO}_2$ indicating that Co is in +3 state. Therefore, during the protonation, $\text{Na}_{0.2}\text{CoO}_2$ gets reduced to $\text{H}_{0.96}\text{Na}_{0.04}\text{CoO}_2$. The lattice parameters of $\text{H}_{0.96}\text{Na}_{0.04}\text{CoO}_2$ ($a = 2.851 \text{ \AA}$, $c = 13.150 \text{ \AA}$) agree well with those reported by Delaplane *et al.*¹⁶ It should be possible to remove Na^+ or K^+ completely by prolonged treatment of the compound in dilute HCl.

However, there is only a small amount of cobalt gets reduced from Co^{4+} to Co^{3+} state in the case of Li ion exchange reaction from $\text{Na}_{0.2}\text{CoO}_2$ to $\text{Li}_{0.26}\text{CoO}_2$. Li ion exchange reaction from $\text{K}_{0.44}\text{CoO}_2$ yielded $\text{Li}_{0.42}\text{CoO}_2$ indicating nearly quantitative ion exchange reaction.

It is important to note that stoichiometric Delafossite-type AgCoO_2 phase has been obtained from $\text{Na}_{0.2}\text{CoO}_2$ or $\text{K}_{0.44}\text{CoO}_2$ with molten AgNO_3 . In this method of ion exchange reaction, all the cobalt in +4 state gets reduced to +3 state. In fact, this ion exchange method turns out to be a simple method to prepare AgCoO_2 .

Figure 3. Powder XRD patterns for (a) $\text{K}_{0.44}\text{CoO}_2$, (b) $\text{H}_{0.98}\text{K}_{0.02}\text{CoO}_2$, (c) $\text{Li}_{0.42}\text{CoO}_2$ and (d) AgCoO_2 .

3.1 XPS studies

X-ray photoelectron spectra of $\text{Co}(2p)$, $\text{K}(2p)$ and $\text{O}(1s)$ core levels from spectra of $\text{K}_{0.44}\text{CoO}_2$, $\text{H}_{0.98}\text{K}_{0.02}\text{CoO}_2$ and AgCoO_2 samples were recorded. XPS of $\text{Co}(2p)$ region from $\text{K}_{0.44}\text{CoO}_2$, $\text{H}_{0.98}\text{K}_{0.02}\text{CoO}_2$ and AgCoO_2 are shown in figure 6a–c respectively. $\text{Co}(2p_{3/2}, 1/2)$ from $\text{K}_{0.44}\text{CoO}_2$ shows peaks due to Co^{3+} and Co^{4+} states with binding energies of $\text{Co}(2p_{3/2})$ at 779.5, 780.5 eV respectively (see figure 6a). The satellite intensity at 6.0 eV below $\text{Co}(2p_{3/2})$ and $\text{Co}(2p_{1/2})$ peaks are absent and the presence of weak satellite at ~9.0 eV below the main peak clearly shows that Co^{3+} and Co^{4+} ions are in low spin state. Contrary to this, $\text{Co}(2p_{3/2}, 1/2)$ peaks from $\text{H}_{0.98}\text{K}_{0.02}\text{CoO}_2$ are sharp and the binding energies of $\text{Co}(2p_{3/2})$ at 780.3 eV agree well with Co in +3 state. Further, small satellite at ~9.0 eV below the main peaks clearly demonstrated that the Co ions are in +3 state with low spin.

Figure 4. Powder XRD pattern for AgCoO_2 ion exchanged from $\text{K}_{0.44}\text{CoO}_2$.

Figure 5. Powder X-ray diffraction pattern for $\text{Na}_{0.27}\text{CoO}_2$ obtained from NaI melt.

Figure 6. X-ray photoelectron spectra of (a) $\text{Co}(2p)$ in $\text{K}_{0.44}\text{CoO}_2$, (b) $\text{Co}(2p)$ in $\text{H}_{0.98}\text{K}_{0.02}\text{CoO}_2$, (c) $\text{Co}(2p)$ in AgCoO_2 .

Figure 7. Resistivity vs temperature plots for (a) Na_{0.20}CoO₂ and (b) AgCoO₂.

The Co(2p) spectra in H_{0.98}K_{0.02}CoO₂ and AgCoO₂ resemble that of Co in Bi₂Sr₃Co₂O₉¹⁷ where Co is in +3 state with low spin. Thus, XPS study confirms that Co, which is in mixed valent +3 and +4 states in K_{0.44}CoO₂ is transformed to Co³⁺ in H_{0.98}K_{0.02}CoO₂. AgCoO₂ also shows Co in +3 state similar to H_{0.98}K_{0.02}CoO₂ (see figure 6c). Ag⁺(3d_{5/2}) peak is observed at 368.0 eV as expected. O(1s) peaks are observed at ~530.0 eV. XPS study thus provides the electronic state of Co in K_{0.44}CoO₂, H_{0.98}K_{0.02}CoO₂ and AgCoO₂ phases.

3.2 Electrical properties

Electrical resistivity measurements were done on the sintered pellets by four-probe method. Figure 7 shows the resistivity vs. temperature plots of (a) Na_{0.2}CoO₂ and (b) AgCoO₂ respectively. Unlike Na_{0.5}CoO₂ which is metallic,¹³ Na_{0.2}CoO₂ sample shows semiconductor to metal like transition at ~100 K and AgCoO₂ compound exhibit semi-conducting behaviour. However, highly semiconducting behaviour of AgCoO₂ is clear from the plot. K_{0.44}CoO₂ showed metallic behaviour from 300 to 20 K similar to K_{0.5}CoO₂.

4. Conclusions

Layered Na_xCoO_2 and K_xCoO_2 phases obtained from molten NaOH and KOH fluxes show the following.

- (a) $\text{Na}_{0.2}\text{CoO}_2$ is obtained where 80% of Co is in +4 state; structure of this phase could not be determined.
- (b) $\text{K}_{0.44}\text{CoO}_2$ is obtained from KOH flux where lattice parameters are close to $\text{K}_{0.5}\text{CoO}_2$ pseudohexagonal phase. However, its structure needs to be determined.
- (c) Both $\text{Na}_{0.20}\text{CoO}_2$ and $\text{K}_{0.44}\text{CoO}_2$ give HCoO_2 and Delafossite-type AgCoO_2 phases. Their structure and properties are the same as those reported in the literature. The study shows that large single crystals of these phases can be easily made by this method.
- (d) Li ion exchange takes place almost to the same extent of Na or K in the parent A_xCoO_2 ($\text{A} = \text{Na}, \text{K}$) phases.
- (e) $\text{Na}_{0.27}\text{CoO}_2$ crystallizing in orthorhombic structure is obtained from NaI flux.

Acknowledgements

We thank the Department of Science and Technology, Government of India, for financial support.

References

1. Fouassier C, Matejka G, Jean-Maurice Reau and Hagenmuller P 1973 *J. Solid State Chem.* **6** 532
2. Balsys R J and Davis R L 1996 *Solid State Ionics* **93** 279
3. Delmas C, Braconnier J J and Hagenmuller P 1982 *Mater. Res. Bull.* **17** 117
4. Takada K, Sakurai H, Muromachi T E, Izumi F, Dilanian RA and Sasaki T 2003 *Nature (London)* **422** 55
5. Groult D, Pannetier J and Raveau B 1982 *J. Solid State Chem.* **41** 277
6. Rice C E and Jackal J L 1982 *J. Solid State Chem.* **41** 308
7. Bhat V and Gopalakrishnan J 1988 *Solid State Ionics* **26** 25
8. Sato K, Hagizuka S and Inoue Y 1993 *Solid State Ionics* **66** 197
9. Nakamura S, Ohtake J, Yonezawa N and Iida S 1996 *J. Phys. Soc. Jpn.* **65** 358
10. Delmas C, Fouassier C and Hagenmuller P 1975 *J. Solid State Chem.* **13** 165
11. Jansen V M and Hoppe R 1974 *Z. Anorg. Allg. Chem.* **408** 97
12. Delmas C, Braconnier J J, Fouassier C and Hagenmuller P 1981 *Solid State Ionics* **3/4** 165
13. Tanaka T, Nakamura S and Iida S 1994 *Jpn J. Appl. Phys.* **B33** L581
14. Vogel A I 1961 *Text book of quantitative inorganic analysis* 3rd edn (London: Longmans) p. 443
15. Stahlin V W and Oswald H R 1969 *Z. Anorg. Allg. Chem.* **367** 206
16. Delaplane R G, Ibers J A, Ferraro J R and Rush J J 1969 *J. Chem. Phys.* **50** 1920
17. Tarascon J.-M, Ramesh R, Barboux P, Hegde M S, Hull G W, Greene L H, Giroud M, LePage Y, McKinnon W R, Waszczak J V and Schneemeyer L F 1989 *Solid State Commun.* **71** 663