Electronic Supplementary Information for Studying a Heme Protein and Bare Metal Porphyrin Complex Immobilized on Functionalized Silicon Surfaces using Synchrotron X – Ray Reflectivity

Rudra N. Samajdar^a, Chandan Kumar^b, P. Viswanath^b Aninda J. Bhattacharyya^{a,}*

^aSolid State and Structural Chemistry Unit, Indian Institute of Science, Bangalore: 560012,
India

^bCenter for Nano and Soft Matter Science, Bangalore: 560013, India

*Corresponding author: anindajb@iisc.ac.in

Contents:

- **Sec. S1. X Ray Reflectivity: Basic Principles**
- **Figure S1. Atomic Force Micrographs of Hemin bilayers on –OH terminated silicon substrates**
- **Figure S2. XRR as a function of momentum transfer for hemin bilayers and multilayers on functionalized silicon substrates.**
- **Figure S3. XRR as a function of momentum transfer for bilayers and multilayers of hemoglobin at pH 7.2 on functionalized silicon substrates.**
- **Figure S4. XRR as a function of momentum transfer for bilayers and multilayers of hemoglobin at pH 9.2 on functionalized silicon substrates.**
- **Section S2. Impedance analysis of functionalized substrates for pK_A determination**
- **References.**

Section S1: X ray reflectivity - basic principles:

We shall briefly touch upon the theory of XRR here as outlined in the literature¹⁻³

Fresnel laws of classical optics describe the specular reflection of X – rays. The complex refractive index for matter for X – rays of wavelength λ is:

$$n = 1 - \delta + i\beta \dots \dots (S1)$$

Here $\delta = \frac{\rho\lambda^2 r_0}{2\pi}$, ρ being the effective electron density, and r_0 the classical electron radius or the Thompson scattering length.

While, $\beta = \frac{\lambda}{4\pi\mu}$ where μ is the x ray absorption length. For the wavelengths at which these experiments are done, δ and $\beta \ll 1$. Effective electron density ρ of materials with low atomic number Z is effectively equal to the total electron density of the material ρ_T . If a fraction of the electrons (f) has binding energies greater than incident x ray energies, then the effective electron density reduces to:

$$\rho = \rho_T(1 - f) \dots \dots (S2)$$

Defining the critical angle as :

$$\phi_c \approx \sqrt{2\delta} = \lambda \sqrt{\frac{\rho r_0}{\pi}} \dots \dots (S3)$$

We can define the expression for Fresnel reflectivity at small angles ϕ using Maxwell's equations as:

$$R_F(\phi) = \left| \frac{\phi - (\phi^2 - \phi_c^2 + i\beta)^{1/2}}{\phi + (\phi^2 - \phi_c^2 + i\beta)^{1/2}} \right|^2 \dots \dots (S4)$$

Transforming to the scattering vector q we get:

$$q = \left(\frac{4\pi}{\lambda} \right) \sin \phi \dots \dots (S5)$$

$$R_F(q) = \left| \frac{q - (q^2 - q_c^2 + \frac{2i}{\mu})^{1/2}}{q + (q^2 - q_c^2 + \frac{2i}{\mu})^{1/2}} \right|^2 \dots \dots (S6)$$

The “critical wave vector” is defined as:

$$q_c \approx \frac{4\pi}{\lambda} \sin \phi_c \dots \dots (S7)$$

This is usually independent of the wavelength in air, and for silicon $q_c = 0.0316 \text{ \AA}^{-1}$. At $q \approx q_c$ there is a rounding of the reflectivity profile due to small absorption. Away from the critical wave vector region, absorption effects are negligible. At q away from q_c , absorption effects are negligible. For $q < q_c$, the reflectivity is almost 100%. Above the critical angle, the reflectivity is given by:

$$R_F(q) \approx \left(\frac{q_c}{2q}\right)^4 \dots \dots \dots (S8)$$

In terms of average electron density, the reflectivity can be modelled as:

$$R(q) = R_F(q)|\phi(q)|^2 \dots \dots \dots (S9)$$

$$\phi(q) = \int \frac{1}{\rho_\infty} \left\langle \frac{d\rho}{dz} \right\rangle e^{iqz} dz \dots \dots \dots (S10)$$

Here $\langle d\rho/dz \rangle$ is the derivative of the electron density profile averaged over the in-plane coherence length of the x rays and ρ_∞ is the electron density of the bulk. The above approximation is valid within the regime of the Born approximation (i.e at $\phi \geq 2\phi_c$ to rule out any refraction effects).

The average electron density of a simple non-functionalized surface can be modelled as a Gaussian:

$$\langle \rho(z) \rangle = \frac{\rho_\infty}{2} \left[1 + \operatorname{erf}\left[\frac{z}{2\sigma}\right] \right] \dots \dots \dots (S11)$$

$$\left\langle \frac{d\rho}{dz} \right\rangle = \rho_\infty \frac{1}{(2\pi\sigma^2)^{1/2}} e^{-\frac{z^2}{2\sigma^2}} \dots \dots \dots (S12)$$

Here σ is the root mean square average of the surface width, governed by both the intrinsic width of the interface as well as the root mean square average of the surface roughness. The Fourier transform of this expression is:

$$R(q) = R_F(q)e^{-\sigma^2 q^2} \dots \dots \dots (S13)$$

This is similar to the Debye – Waller factor in crystallography.

The experimentally obtained reflectivity profile is fit with an electron density model based on the chemical nature of the interface. The electron density profile provides valuable information about the structure and orientation of molecules on the interface. Thus, x ray reflectivity is very useful in understanding the properties of molecules at interfaces.

Figure S1: Atomic Force Micrographs of (anticlockwise from top): -OH functionalized silicon substrate, protein bilayers on this substrate; hemin bilayer on this substrate.

Figure S2: X ray reflectivity as a function of momentum transfer for (top) hemin bilayers (Langmuir Blodgett) and (bottom) hemin multilayers (absorption) on silicon substrates with different hydrophobic and hydrophilic functionalizations.

Figure S3: X ray reflectivity as a function of momentum transfer for (top) hemoglobin bilayer (Langmuir Blodgett) at pH 7.2; (bottom) hemoglobin multilayer (absorption) at pH 7.2 on different hydrophilic and hydrophobic functionalized silicon substrates.

Figure S4: X ray reflectivity as a function of momentum transfer for (top) hemoglobin bilayer (Langmuir Blodgett) at pH 9.2 and (bottom) hemoglobin multilayer (absorption) at pH 9.2 for hydrophobic and hydrophilic surfaces.

Section S2:

Interfacial capacitance measurements as a function of pH can reveal information about surface absorbed molecules.⁴

$$\frac{1}{C_T} = \frac{1}{C_F} + \frac{1}{\{C_S + C(f)\}}$$

Here C_T is the total interfacial capacitance, C_F is the film capacitance, C_S is the diffuse layer capacitance, C_f is the degree of protonation. At pH close to the pK of the surface molecule, the capacitance is expected to show a maximum.⁵

We measure impedance spectra of the $-\text{NH}_2$ and COOH functionalized substrates as a function of applied potential. Capacitance values are extrapolated from the Bode plot at $\omega = 0$.

The capacitance versus pH plot for $-\text{COOH}$ functionalized substrates is shown below:

Figure S5: Variation of capacitance with pH for $-\text{COOH}$ functionalized surface.

We see a maxima close to 5.7 which conforms with the pK_A value of 5.5 reported in the literature.

The conjugate acid of the $-\text{NH}_2$ groups in the amine functionalized surfaces is expected to have a very high pK_A (10.37 as pK_B is 3.63 for the base). However since we do not study proteins at such high pH in this paper, we can assume that the $-\text{NH}_2$ groups are well protonated in our working pH window.

References:

1. Tidswell, I. M.; Ocko, B. M.; Pershan, P. S.; Wasserman, S. R.; Whitesides, G. M.; Axe, J. D. X-Ray Specular Reflection Studies of Silicon Coated by Organic Monolayers (Alkylsiloxanes). *Physical Review B* **1990**, *41*, 1111-1128.
2. Pietsch, U.; Holy, V.; Baumbach, T. *High Resolution X Ray Scattering from Thin Films to Lateral Nanostructures*. 2nd Edition ed.; Springer Verlag: New York, 2004.
3. Als-Nielsen, J.; McMorrow, D. *Elements of Modern X Ray Physics*. 2nd Edition ed.; John Wiley and Sons: 2011.
4. Bryant, M. A.; Crooks, R. M. Determination of Surface Pka Values of Surface-Confining Molecules Derivatized with Ph-Sensitive Pendant Groups. *Langmuir* **1993**, *9*, 385-387.
5. Smith, C.; White, H. Voltammetry of Molecular Films Containing Acid/Base Groups. *Langmuir* **1993**, *9*, 1-3.